


## T. B. C. TRI BUTYL CITRATE

*C<sub>18</sub>H<sub>32</sub>O<sub>7</sub>*



T.B.C. is a very good plasticizer for PVC and cellulosic derivatives. T.B.C. improves light stability and it has good solvating properties for rubber and PVC. Since it has good low temperature properties and also is a non-toxic plasticizer, it can be used in food contact applications.

PROPERTIES	VALUE	UNIT
Density (20°C )	1,035-1,045	gr/cm <sup>3</sup>
Refractive Index (20°C )	1,443-1,445	
Acidity	0,5 Max.	mgKOH/g
Viscosity (20°C )	33-35	mPa.s
Flash Point	> 180	°C
Ester Content	99,5 Min.	%
Water Content	0,4 Max.	%
Colour	40 Max.	Hazen
Cas No	77-94-1	
EC No	201-071-2	

